

Amercoat 383H

High-build epoxy intermediate coating

Product Data/ Application Instructions

- High build epoxy intermediate coating
- Reduced volatile organic compounds (VOC)
- High-build and High-solids
- Tough and durable
- Also available with 40% MIO pigmentation

Typical uses

Amercoat 383H is used as an intermediate coating for atmospheric exposure in marine and industrial environments. Amercoat 383H is normally applied over an inorganic zinc-silicate or epoxy primer

Typical Global Systems using Amercoat 383H

ISO 12944 classification	First coat	Intermediate	Finish Coat
C5	Dimetcote	Amercoat 383H	Amercoat 450 Series
C5	Amercoat 68 Series	Amercoat 383H	Amercoat 450 Series
C4	Amercoat 385PA	Amercoat 383H	Amercoat 450 Series

Amercoat 383H is not recommended for direct to metal applications, for use at continuous immersion conditions and is normally topcoated for optimal performance

Approvals and Certificates

Amercoat 383H has been successfully tested to/ and meets the requirements of Norsok M501-rev.5 system1 as an intermediate coating in conjunction with Amercoat 68G primer and Amercoat 450 series topcoats. Consult your PPG representative for full system details.

Physical Data

Finish.....	semi gloss	
Colour.....	Off White, Light Grey, MIO Pearl Grey, GR-3	
Components	2	
Mixing ratio (by volume)	1 part Resin 1 part Cure	
Curing mechanism	solvent release and chemical reaction between components	
Volume solids	77% (ISO 3233)*	
VOC**		
EC SED 1999/13/EC	148 g/kg (225 g/l)	
UK PG6/23(92) Appendix 3	180 g/l (1.5 lbs/gal)	
Dry film thickness	100 – 200 µm per coat 4 –8 mil per coat	
Number of coats	1	
Theoretical coverage		
At 100 microns/4 mil dft	7.7 m ² /l	314 ft ² /gal
At 200 microns/6 mil dft	3.80 m ² /l	157 ft ² /gal
Flashpoints	°C	°F
Cure	47	117
Resin	47	117
Mixed	47	117
Amercoat 65	24	75
Amercoat 12	24	75
Thinners	Amercoat 65	
Cleaner.....	Amercoat 12	

* Volume solids is measured in accordance with ISO 3233. Slight variations ±3% may occur due to colour and testing variances.

** VOC figures are quoted according to both the EC directive 1999/13/EC which are theoretically calculated figures and the UK PG6/23(92) Appendix 3 which are practically determined figures.

Amercoat 383H

Caution

This product is flammable. Keep away from heat and open flame. Keep container closed. Use with adequate ventilation. Avoid prolonged and repeated contact with skin. If used in confined areas, observe the following precautions to prevent hazards of fire or explosion or damage to the health:

1. circulate adequate fresh air continuously during application and drying;
 2. use fresh air masks and explosion proof equipment;
 3. prohibit all flames, sparks, welding and smoking.
- Do not empty into drains. Take precautionary measures

against static discharges. For specific information on hazardous ingredients, required ventilation, possible consequences of contact and safety measures see

Safety
Data Sheet

Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

Warranty

PPG warrants its products to be free from defects in material and workmanship. PPG's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at PPG's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

PPG makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall PPG be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by PPG, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

Limitation of Liability

PPG's liability on any claim of any kind, including claims based upon PPG's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim. In no event shall PPG be liable for consequential or incidental damages.

Due to PPG's policy of continuous product improvement, the information contained in this Product Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product Data/Application Instructions always refer to the PPG Protective & Marine Coatings website at www.ppgpmc.com

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.

